

SR3, SRH3

Krimpbuis dikwandig

halogeen-vrij krimpverhouding 3:1 met of zonder thermoplastische lijm



Produktbeschrijving

Artikelbeschrijving	SR3 55-15
Artikelnummer	144620
Notities	Andere lengtes op aanvraag
Eigenschappen	Dikwandig
	Beschrijfbaar
	Bestand tegen chemische invloeden
	Bestand tegen UV-stralen
	Vrij van oplosmiddelen Eigenschappen
	Niet corrosief
	Niet smeltbaar
	Halogeenvrij
	Zeer goede elektrische eigenschappen
	Hoge trekvastheid
	Koudvloeibestendig (thermisch vormstabiel)
Toepassing	Isoleren
	Druk- en vochtbescherming
	Geschikt voor krimpmoffen en krimpeindsluitingen

Technisch Gegevensblad

Technische gegevens

Artikelbeschrijving	SR3 55-15
Artikelnummer	144620
Testrapporten	IEC 60684-2
Materialen	Gemodificeerde polyolefin
	Lood- en cadmiumvrij
Selectie Opmerking	zonder lijm
Lengte L	1 m
Kleuren	zwart
Inner diameter before shrinking (mm)	55 mm
Inner diameter after shrinking (mm)	15 mm
Recovered wall thickness	4.4 mm
Hardness	55 Shore D
Hardness(associated standard)	DIN 53505
Elongation at break	350 %
Elongation at break (associated standard)	IEC 60684-2
Tensile strength at break	13 MPa
Tensile strength at break (associated standard)	IEC 60684-2
Longitudinal shrinkage	+/- 10 %
Longitudinal shrinkage (associated standard)	IEC 60684-2
Shrink ratio	3 : 1
Shrink ratio (associated standard)	IEC 60684-2
Eccentricity expanded	50 %
Eccentricity recovered	85 %
Eccentricity (associated standard)	IEC 60684-2
Operating temperature range min	-40 °C
Operating temperature range max	120 °C
Operating temperature range (associated standard)	IEC 60684-2
Shrinkage temperature	> 125 °C
Burning behaviour	niet zelfdovend
Burning behaviour (associated standard)	IEC 60684-2
Flexibility at low temperatures	-40 °C
Flexibility at low temperatures (associated standard)	IEC 60684-2
Thermal ageing (168 h at 150 °C): Elongation at break	250 %
Thermal ageing (168 h bei 150 °C): Tensile strength at break	12 MPa
Thermal ageing (168 h bei 150 °C) (associated standard)	IEC 60684-2
Specific volume resistivity	10 ¹⁴ Ω cm
Specific volume resistivity (associated standard)	IEC 60684-2
Dielectric strength	25 kV/mm
Dielectric strength (associated standard)	IEC 60684-2
Corrosion	geen
Corrosion (associated standard)	IEC 60684-2
Resistance to fungus and decay	Tarief 1
Resistance to fungus and decay (associated standard)	IEC 60684-2

Technisch Gegevensblad

Logistieke gegevens

Artikelbeschrijving	SR3 55-15
Artikelnummer	144620
Levering	Warmtekrimpbuis dikke wand als secties
Duurzaamheid aanvullende teksten	Onbeperkt houdbaar
Douanetariefnummer	39173200
EAN/GTIN	4010311024660

Verpakkingsgegevens

Alternatieve maateenheid	Stuk	Zak1	Zak	Pak
Basishoeveelheid	1	1	10	10
Basis maateenheid	Stuk	Stuk	Stuk	Stuk
Lengte (mm)	1000	1000	1030	1030
Breedte (mm)	72	72	280	280
Hoogte (mm)	45	45	110	110
Netto gewicht (kg)	0.247	0.247	2.47	2.47
Bruto gewicht (kg)	0.247	0.247	2.475	2.475