

## K224-HG6

## PA6-GF30

### RHEOLOGICAL PROPERTIES

Properties	Typical Data	Unit	Test Method
Molding shrinkage (parallel)	0.3/*	%	ISO 294-4
Molding shrinkage (normal)	0.9/*	%	ISO 294-4

### MECHANICAL PROPERTIES

Properties	Typical Data	Unit	Test Method
Tensile modulus	9500/6000	MPa	ISO 527-1/-2
Stress at break	180/110	MPa	ISO 527-1/-2
Stress at break	3.5/7	%	ISO 527-1/-2
Flexural modulus	8600/-	MPa	ISO 178
Flexural strength	235/-	MPa	ISO 178
Charpy impact strength (+23 °C)	90/110	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30 °C)	75/75	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23 °C)	12/25	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30 °C)	11/11	kJ/m <sup>2</sup>	ISO 179/1eA

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specification.

#### ESDEC bv

Londenstraat 1 6  
7418 EE Deventer  
The Netherlands

T +31 850 702 000  
info@esdec.com  
www.esdec.com

IBAN NL64 INGB 0658539531  
BIC INGBNL2A  
BTW NL813998955B01



## K224-HG6

## PA6-GF30

### THERMAL PROPERTIES

Properties	Typical Data	Unit	Test Method
Melting temperature (10 °C/min)	220/*	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200/*	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220/*	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2/*	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.7/*	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5mm nom. thickn.	HB/*	class	IEC 60695-11-10
Thickness tested	1.5/*	mm	IEC 60695-11-10
Burning Behav. at thickness h	HB/*	class	IEC 60695-11-10
Thickness tested	0.75/*	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	700/-	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	2/-	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	700/-	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	1.5/-	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	725/-	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	2/-	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	725/-	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	1.5/-	mm	IEC 60695-2-13

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specification.

#### ESDEC bv

Londenstraat 1 6  
7418 EE Deventer  
The Netherlands

T +31 850 702 000  
info@esdec.com  
www.esdec.com

IBAN NL64 INGB 0658539531  
BIC INGBNL2A  
BTW NL813998955B01



## K224-HG6

### PA6-GF30

#### ELECTRICAL PROPERTIES

Properties	Typical Data	Unit	Test Method
Relative permittivity (100Hz)	3.5/20	-	IEC 60250
Relative permittivity (1 MHz)	3.3/5	-	IEC 60250
Dissipation factor (100 Hz)	50/3000	E-4	IEC 60250
Dissipation factor (1 MHz)	150/1200	E-4	IEC 60250
Volume resistivity	1E12/1E10	Ohm*m	IEC 60093
Surface resistivity	*/1E13	Ohm	IEC 60093
Electric strength	30/15	kV/mm	IEC 60243-1
Comparative tracking index	*/500	-	IEC 60112

#### ELECTRICAL PROPERTIES

Properties	Typical Data	Unit	Test Method
Water absorption	6.3/*	%	Sim. to ISO 62
Humidity absorption	1.9/*	%	IEC 60250
Density	1350/-	kg/m <sup>3</sup>	ISO 1183

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specification.

#### ESDEC bv

Londenstraat 1 6  
7418 EE Deventer  
The Netherlands

T +31 850 702 000  
info@esdec.com  
www.esdec.com

IBAN NL64 INGB 0658539531  
BIC INGBNL2A  
BTW NL813998955B01

